



SPECIFICATION DATA

1. Product Name

Versi-Foam® Systems 10 and 33 Disposable Foam Kits

2. Manufacturer

RHH FOAM SYSTEMS, INC.
17100 W. Victor Road | New Berlin, WI 53151
Phone: 1-800-657-0702 | 262-754-8088
Fax: 262-754-8089
Email: sales@rhhfoamsystems.com
Website: www.rhhfoamsystems.com

3. Product Description

Versi-Foam® Systems 10 and 33 are disposable closed-cell foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-CONTROL dispensing gun, ten multi-purpose mixing nozzles, nitrile gloves, and packet of petroleum jelly. They require no external power source.

4. Technical Data

Versi-Foam® Systems 10 and 33 have the following physical properties:

DENSITY (ASTM D1622):

Free Rise	2.8 lb/ft ³
In Place	3.0 lb/ft ³

R FACTOR (ASTM C518): 7.7/inch

COMPRESSIVE STRENGTH (ASTM D1621): 26 psi (parallel)

WATER ABSORPTION (ASTM D2127): 0.009 lb/ft²

CLOSED CELL CONTENT (ASTM D2856): >90%

DIMENSIONAL STABILITY (ASTM D2126):

% Volume Change, 158°F, 100 RH, 7 days	3.75
% Volume Change, -80°F, 7 days	0.03

TEMPERATURE TOLERANCE:

High Temperature Tolerance	250° F
Low Temperature Tolerance	-250° F

FLAMESPREAD (ASTM E84): N/A

SMOKE DEVELOPED (ASTM E84): N/A

TACK FREE TIME: 30-40 seconds

RISE TIME: 30-40 seconds

YIELD:

System 10	10 ft ³ 120 ft ² @ 1" thick
System 33	33 ft ³ 396 ft ² @ 1" thick

- Versi-Foam® products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.
- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Versi-Foam® Systems.