

# **SPECIFICATION DATA**

### 1. Product Name

Versi-Foam® Systems 10 and 33 Disposable Foam Kits

## 2. Manufacturer

RHH Foam Systems, Inc. 5500 South Westridge Drive | New Berlin, WI 53151 Phone: 1-800-657-0702 | 262-754-8088 Fax: 262-754-8089 Email: sales@rhhfoamsystems.com Web: www.rhhfoamsystems.com



#### 3. Product Description

Versi-Foam<sup>®</sup> Systems 10 and 33 are high density, disposable, closed-cell, low-pressure spray foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, ten multi-purpose mixing nozzles, nitrile gloves, and packet of petroleum jelly. They do not require any external power source.

#### 4. Technical Data

Versi-Foam<sup>®</sup> Systems 10 and 33 have the following physical properties:

#### DENSITY (ASTM D1622):

Free Rise	2.8 lb/ft <sup>3</sup>
In Place	3.0 lb/ft <sup>3</sup>
R FACTOR at 1" thickness (ASTM C518):	7.7
COMPRESSIVE STRENGTH (ASTM D1621):	26 psi (parallel)
WATER ABSORPTION (ASTM D2127):	0.009 lb/ft <sup>2</sup>
CLOSED CELL CONTENT (ASTM D2856):	>90%
DIMENSIONAL STABILITY (ASTM D2126):	•
% Volume Change, 158°F, 100 RH, 7 days	3.75
% Volume Change, -80°F, 7 days	0.03
TEMPERATURE TOLERANCE:	
High Temperature Tolerance	250° F
Low Temperature Tolerance	-250° F
FLAMESPREAD (ASTM E84):	N/A
SMOKE DEVELOPED (ASTM E84):	N/A
TACK FREE TIME:	30-40 seconds
RISE TIME:	30-40 seconds
YIELD:	
System 10	10 ft <sup>3</sup>   120 ft <sup>2</sup> @ 1" thick
System 33	33 ft <sup>3</sup>   396 ft <sup>2</sup> @ 1" thick

• Versi-Foam<sup>®</sup> products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.

- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Versi-Foam<sup>®</sup> Systems.