

# **SPECIFICATION DATA**

## 1. Product Name

Versi-Foam® Systems 31 and 100 Class I Open Cell Foam Kits

## 2. Manufacturer

RHH Foam Systems, Inc. 5500 South Westridge Drive | New Berlin, WI 53151 Phone: 1-800-657-0702 | 262-754-8088 Fax: 262-754-8089 Email: sales@rhhfoamsystems.com Web: www.rhhfoamsystems.com



### 3. Product Description

The Versi-Foam® Systems 31 and 100 are open cell portable and disposable low-pressure spray foam kits. They include two sets of chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, ten multi-purpose mixing nozzles, nitrile gloves, and a packet of petroleum jelly. The Versi-Foam® Systems 31 and 100 contain a flame retardant formula, meeting requirements of ASTM E-84 as Class I products. They are pre-pressurized and require no external power source.

The appeal of low-density, open cell products like the Versi-Foam<sup>®</sup> Systems 31 and 100 is their high expansion rate, making them less expensive per board foot than closed cell foams. These systems offer a cost effective means to insulate, control air movement and reduce sound transmission between rooms within the building. The Systems 31 and 100 are also well suited for exterior wall applications in which one inch of closed cell foam is applied to the exterior sheathing and then filled with open cell foam.

### 4. Technical Data

The Versi-Foam® System 31 and 100 Class I Open Cell have the following physical properties:

DENSITY (ASTM D1622):	0.75 lb/ft <sup>3</sup>	
R FACTOR at 1" thickness (ASTM C518):	4.0	
CLOSED CELL CONTENT (ASTM D2856):	8%	Versi-Foam® products do not contain
OPEN CELL CONTENT (ASTM D2856):	92%	any CFC's, Penta-BDE's, VOC's, or Urea- Formaldehyde.
TEMPERATURE TOLERANCE:		
High Temperature Tolerance	250° F	<ul> <li>Published yields are theoretical and</li> </ul>
Low Temperature Tolerance	-250° F	vary based on several factors, including
AIR PRESSURE PROPERTIES (ASTM E283):		ambient conditions and specific application.
Infiltration, 75 Pa	0.0013 L/s/m <sup>2</sup>	app
Exfiltration, 75 Pa	0.0015 L/s/m <sup>2</sup>	<ul> <li>Always use recommended personal</li> </ul>
FLAMESPREAD at 2" thickness (ASTM E84):	25	protective equipment when using
SMOKE DEVELOPED at 2" thickness (ASTM E84):	300	polyurethane foam products. Refer to the Material Safety Data Sheet for
TACK FREE TIME:	2 minutes	additional information on safe use and
RISE TIME:	2 minutes	handling of Versi-Foam® Systems.
YIELD:		
System 31	380 ft <sup>2</sup> @ 1" thick	
System 100	1,200 ft <sup>2</sup> @ 1" thick	